

# BauderKOMPAKT ULK

## Technical data sheet

Type of application:	<b>Elastomer bitumen waterproofing membrane as underlayer</b>		
Surface	top:	<b>Foil, Sand</b>	
	bottom:	<b>Sand</b>	
reinforcement	Type and weight:	<b>Polyester fleece 250 g/m<sup>2</sup></b>	
Article number	<b>1785 0000</b>		

Characteristic	Test method	Unit	Value
length	DIN EN 1848-1	m	10
width	DIN EN 1848-1	m	1
Minimum of solubility	DIN 52 123	g/m <sup>2</sup>	≥ 2100
thickness	DIN EN 1849-1	mm	nvs
Flexibility at low temperature	DIN EN 1109	°C	≤ -30
Flow resistance at elevated temperature	DIN EN 1110	°C	≥ +100
Tensile properties: max. tensile force	DIN EN 12311-1	N / 50 mm	length: ≥ 800      transverse: ≥ 800
Tensile properties: elongation	DIN EN 12311-1	%	length: ≥ 35      transverse: ≥ 35
straightness	DIN EN 1848-1	mm / 10m	≤ 20
watertightness type A and T	DIN EN 1928 Verf. B	-	passed
Reaction to fire	DIN EN ISO11925-2	-	class E according to DIN EN 13501-1
External fire performance	DIN V ENV 1187	-	passed*
Visible defects	DIN EN 1850-1	-	no visible defects
Peel resistance of joint	DIN EN 12316-1	N / 50 mm	nvs
Shear resistance of joint	DIN EN 12317-1	N / 50 mm	nvs
Resistance to impact	DIN EN 12691	mm	nvs
Resistance to static loading	DIN EN 12730	kg	nvs
Dimensional stability	DIN EN 1107-1	%	nvs
Artificial ageing DIN EN 1296	DIN EN 1109	°C	nvs
	DIN EN 1110	°C	

nvs = no value specified

\* tested in system

The declared values are determined statistically and are subject to tolerances.



Identification number of the certification body: 1724  
 Certificate number: 021101/ 021201  
 (06)  
**DIN EN 13707, DIN EN 13969**